

Technical Datasheet – Carbon Woven Reinforcement Fabric

HinFab™ HAP170

170 GSM – Plain Woven Aramid Fabric



Characteristic	Specification	Tolerance	Test Method
Areal Weight (g/m ²)	170	± 3%	ASTM D3801
Width* (mm)	1000	-0/+10mm	ASTM D3774
Dry Fabric Thickness(mm)	0.25	± 0.03mm	ASTM D1777

*Custom Width available.

	High Modulus		
	19.6 ends/inch		
WEFT	Aramid Fiber	50% by weight	
	High Modulus		
	19.6 picks/inch		

Fiber Properties	
Density (g/cm ³)	1.44
Filament Diameter (µm)	12
Tensile Strength (MPa)	3176
Tensile Modulus (GPa)	108
Elongation (%)	2.8
Sizing	Epoxy Compatible

Typical Packaging
Wound on a cardboard tube, sealed in a polyethylene bag, firmly secured and placed in a cardboard box

Disclaimer
HinFab™ fabrics are manufactured in accordance with Hindoostan Composite Solutions written and published data. A Certificate of Conformance is provided with each shipment.

Sir Vithaldas Chambers 16, Mumbai Samachar Marg, Mumbai 400001, India.

www.hindoostantech.com Email: contact@hindoostantech.com