

# Technical Datasheet – Carbon Woven Reinforcement Fabric

HinFab™ HAP223

220 GSM – Plain Woven Aramid Fabric



Characteristic	Specification	Tolerance	Test Method
Areal Weight (g/m <sup>2</sup> )	220	± 3%	ASTM D3801
Width* (mm)	1000	-0/+10mm	ASTM D3774
Dry Fabric Thickness(mm)	0.32	± 0.03mm	ASTM D1777

\*Custom Width available.

<b>WARP</b>	Aramid Fiber	50% by weight	
	High Modulus		
	16.50 ends/inch		
<b>WEFT</b>	Aramid Fiber	50% by weight	
	High Modulus		
	16.50 picks/inch		

Fiber Properties	
Density (g/cm <sup>3</sup> )	1.44
Filament Diameter (μm)	12
Tensile Strength (MPa)	3097
Tensile Modulus (GPa)	105
Elongation (%)	2.8
Sizing	Epoxy Compatible

Typical Packaging
Wound on a cardboard tube, sealed in a polyethylene bag, firmly secured and placed in a cardboard box

Disclaimer
HinFab™ fabrics are manufactured in accordance with Hindoostan Composite Solutions written and published data. A Certificate of Conformance is provided with each shipment.

Sir Vithaldas Chambers 16, Mumbai Samachar Marg, Mumbai 400001, India.

www.hindoostantech.com Email: [contact@hindoostantech.com](mailto:contact@hindoostantech.com)