

# Technical Datasheet – Carbon Woven Reinforcement Fabric

**HinFab™ HGU900**

*900 GSM – Uni Directional Glass Fabric*



Characteristic	Specification	Tolerance	Test Method
Areal Weight (g/m <sup>2</sup> )	900	± 3%	ASTM D3801
Width* (mm)	500	-0/+10mm	ASTM D3774
Dry Fabric Thickness(mm)	0.65	± 0.03mm	ASTM D1777

\*Custom Width available.

<b>WARP</b>	Glass Fiber	98% by weight	
	Advantex® E-Glass SE 1200		
	9.50 ends/inch		
<b>WEFT</b>	Glass Fiber	2% by weight	
	Advantex® E-Glass SE 1200		
	4.00 picks/inch		

Fiber Properties	
Density (g/cm <sup>3</sup> )	2.62
Filament Diameter (µm)	17
Tensile Strength (MPa)	3750
Tensile Modulus (GPa)	80
Elongation (%)	4.8
Sizing	Epoxy Compatible

Typical Packaging
Wound on a cardboard tube, sealed in a polyethylene bag, firmly secured and placed in a cardboard box

Disclaimer
HinFab™ fabrics are manufactured in accordance with Hindoostan Composite Solutions written and published data. A Certificate of Conformance is provided with each shipment.

Sir Vithaldas Chambers 16, Mumbai Samachar Marg, Mumbai 400001, India.

[www.hindoostantech.com](http://www.hindoostantech.com) Email: [contact@hindoostantech.com](mailto:contact@hindoostantech.com)